



US006638892B1

(12) **United States Patent**
Wu et al.

(10) **Patent No.:** **US 6,638,892 B1**
(45) **Date of Patent:** **Oct. 28, 2003**

(54) **SYNGAS CONVERSION AND CATALYST
SYSTEM EMPLOYED THEREFOR**

(75) Inventors: **An-hsiang Wu**, Kingwood, TX (US);
Jianhua Yao, Bartlesville, OK (US);
Charles A. Drake, Nowata, OK (US)

(73) Assignee: **ConocoPhillips Company**, Houston,
TX (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **10/125,661**

(22) Filed: **Apr. 18, 2002**

(51) **Int. Cl.**⁷ **B01J 23/00**; B01J 29/08;
B01J 21/16; B01J 27/14; B01J 27/182

(52) **U.S. Cl.** **502/307**; 502/306; 502/314;
502/318; 502/79; 502/80; 502/208; 502/214

(58) **Field of Search** 502/306, 318,
502/314, 80, 79, 208, 214, 307

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,911,041 A	10/1975	Kaeding et al.
4,375,424 A	3/1983	Slaugh
4,423,155 A	12/1983	Bell et al.
4,499,327 A	2/1985	Kaiser
4,536,485 A	8/1985	Topp-Jorgensen
4,590,176 A	5/1986	Hoek et al.
4,613,720 A	9/1986	Bonifaz et al.
4,849,575 A	7/1989	Lewis
5,182,242 A	1/1993	Marler
5,191,141 A	3/1993	Barger et al.
5,218,003 A	6/1993	Lewnard et al.
5,684,213 A	11/1997	Nemphos et al.

5,714,662 A	2/1998	Vora et al.	
6,048,816 A	*	4/2000	Brown et al. 502/77
6,137,022 A	*	10/2000	Kuechler et al. 585/638
6,147,125 A	*	11/2000	Shikada et al. 518/713

OTHER PUBLICATIONS

Decanio et al, Acid Catalysis by Dealuminated Zeolite-Y,
Journal of Catalysis 101, 132-141 (1986).*

* cited by examiner

Primary Examiner—J. Parsa

(74) *Attorney, Agent, or Firm*—Ryan N. Cross

(57) **ABSTRACT**

A process for the conversion of syngas by contact of syngas under conversion conditions with catalyst having as components zinc oxide, copper oxide, aluminum oxide, Y zeolite and clay in which (A) in a one step process for conversion of syngas to dimethyl ether, the catalyst has as components an extruded mixture of zinc oxide, copper oxide, gamma aluminum oxide, Y zeolite and clay; (B) in a two step process for conversion of syngas to light olefins, a catalyst system is employed that has in the first step a catalyst mixture of zinc oxide, copper oxide, aluminum oxide, Y zeolite and clay and the catalyst employed in the second step is SAPO-34; SAPO-34 modified with lanthanum(III) nitrate hexahydrate; SAPO-34 modified with magnesium nitrate hexahydrate; SAPO-34 modified with tributyl borate or SAPO-34 modified with triethyl phosphate or (C) in a two step process for conversion of syngas to light olefins, the pressure on the effluent from the contact of syngas with a mixture of zinc oxide, copper oxide, aluminum oxide, Y zeolite and clay is reduced before contact with a second catalyst of SAPO-34. The catalyst systems employed in the processes herein.

8 Claims, No Drawings